

SC-700H

For Hard-facing

Conformances

JIS Z3326 YF3B-C-700


Applications

- Rollers, shear blades, screw conveyer etc.

Features

- Flat and horizontal fillet position welding
- Suitable for abrasion parts

Welding Position



Current

DC +

Shielding Gas

100% CO₂ / FCAW process

Diameter / Packaging

Diameter	Spool
mm (in)	15kg (33lbs)
1.2 (0.045)	√
1.4 (0.052)	√
1.6 (1/16)	√

Typical Chemical Composition of All-Weld Metal (%)

C	Si	Mn	Cr	Mo	V	W	Others
0.5	0.7	1.7	5.2	-	-	0.4	-

Typical Mechanical Properties of All-Weld Metal

Hardness (Hv)

660-720

Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)
1.2mm (0.045 in) DC+					
100% CO ₂	20 (4/5)	9.8 (385)	230	25-27	4.4 (9.7)
		12.5 (492)	260	27-29	5.4 (11.9)
		14.2 (559)	300	29-31	6.3 (13.8)
1.6mm (1/16 in) DC+					
100% CO ₂	20 (4/5)	5.8 (228)	260	27-29	5.1 (11.2)
		7.9 (311)	300	28-30	5.9 (13.0)
		9.7 (381)	330	29-31	7.4 (16.3)