

# ST-347

18%Cr-8%Ni-Nb(STS 347) & 18%Cr-8%Ni-Ti(STS 321)

## Conformances

AWS A5.9/ ASME SFA5.9 ER347

JIS Z3321 YS347

EN ISO 14343-A W 199 Nb

## Applications

- Welding of boiler and gas turbine

## Features

- Resistance to crack is good
- Nb contents improves corrosion resistance and heat resistance

## Current

DC -

## Shielding Gas

Ar

## Diameter / Packaging

Diameter	
mm (in)	5kg*1000
1.0 (0.039)	
1.2 (0.045)	
1.6 (1/16)	✓
2.0 (5/64)	✓
2.4 (3/32)	✓
2.6 (0.10)	✓
3.2 (1/8)	✓

## Typical Chemical Composition of the Wire(%)

C	Si	Mn	Cr	Ni	Nb
0.05	0.43	1.66	20.0	9.6	0.7

## Typical Mechanical Properties of All-Weld Metal

TS	EL
MPa(lbs/in <sup>2</sup> )	(%)
680 (98,600)	32